



dipping



application by brush



flow coating



for windows



for doors



limited dimension  
stable wooden  
constructions



non dimension  
stable wooden  
constructions



stir before use



water thinnable



store and transport  
in a frost free area



store in a cool place



cleaning of  
equipment with  
water



wear protective  
gloves



Wear protective  
mask

**sikkens**  
WOOD COATINGS

## Cetol WV 885 BPD+

**Product description** Waterborne impregnation (fluid timber protecting agent) for a protection against blue stain fungi and rot of none statically subjected wooden constructions without earth contact (windows, shutters, pergola, claddings etc.), exterior.  
- ready to use  
- deep penetration  
- good run-off properties  
- neutral odour

**Active ingredient** The active substances are notified acc. guideline 98/8/EG and correspond to the specification EN 599 against blue stain and rot fungi.

0,6 g/100 g Propinylbutylcarbamate iodine

0,9 g/100 g Propiconazole

0,3 g/100 g Tebuconazole

BAUA-register Nr. 40654

Wood protection agents must be registered according to the BPD. (BPD = Biocide Product Directive)

**Uptake consumption** The examination follows the uptake value: 120-160 ml/m<sup>2</sup> i.e. 123-164 g/m<sup>2</sup> for timber in the resistance classes 3-5

**Colour** Colorless

**Binder type** Acrylic Copolymer

**Packaging** 2.5 l, 20 l, 120 l

**Processing** dipping, flow-coating, brushing

Working viscosity is approx. 11 seconds in a DIN cup 4 mm i.e. approx. 23 - 25 seconds in a ISO cup 3 mm at 20° C material temperature.

**Consumption** 50 - 160 ml/m<sup>2</sup>, depending on application method, type and absorption properties of wood (exact values must be established through a sample)

**Thinning** Do not thin down

**Application temperature** 15 - 25 °C for substrate, air and material at approx. 60 % R.H.

**Drying times** Drying at 23 °C / 50 % R.H.

Dust dry: after approx. 60 minutes

Recoatable: after approx. 4 - 6 hours waterborne

**Cleaning of equipment** Clean directly after use with water, if needed with washing up liquid or with ST 830.

**Storage** A dipping tank containing material must be covered correctly and stirred or circulated regularly.

The minimum storage stability of sealed containers is 2 years.

Storage temperature: +5 - +30 °C.

After ending of the storage time the product still can be usable, but some attributes may vary from new product.

Therefore such over-stored product has to be applied with special attention.

Opened cans must be sealed correctly! Store in a cool but frost-protected area.

**Disposal** Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 03 02 02.

**Hazard identification** In accordance with EC guide lines - Material safety data sheet, point 15.

**Warning** The Impregnation serves as a protection of none statically subjected wooden constructions without earth contact, exterior, against blue stain and rot according to DIN 68800, part 3.

Not for use with wood which has got direct contact with food or food preparation. Only for the use of qualified enterprises

Dipping tanks or reservoirs: when using metal reservoirs, we recommend using None rusting steel i.e. V2A, the use of other materials can lead to corrosion.

Biocide products must be handled carefully

Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

Not to be used near waterways. The fluid must not enter water. Wood preservatives contain biozid substances for the protection against pest control. They are only to be used according to instructions and in permitted working areas.

Misuse can lead to a hazard to health.

**General instructions** The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %.

According to the guidelines for window coating systems, published by the Federal German Committee for Paint and Material Value Protection (Instruction Leaflet No. 18), of VOB, Part C, DIN 18363, and the recommendations of the German Institute for Window Technology e.V. in Rosenheim, all wooden constructions in buildings must be coated on all sides with at least one primer and one intermediate coat (minimum dry film thickness 30 µm) before they are incorporated in buildings. The choice and use of the coating system, especially the colour shade, should also be taken into account. Darker shades can increase the surface temperature (up to 80 C).

For use in a technical industrial companies and exclusively released for Sikkens systems recommendations.

**VOC guideline** Out of scope.

**Relevant information** The the denibbing process may only be made after the following coating system.

The here mentioned coating system is only an example, other systems are possible.

Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ

Bus Pk

UNITED KINGDOM

Tel. +44 1254 687950

Fax. +44 1254 687960

Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ

Bus Pk

Rep of IRELAND

Tel. +35 (0) 21 4220222

Fax. +35 (0) 21 4220205

Akzo Nobel Wood Coatings GmbH Düsseldorf StraÙe 96-100

D-40721 Hilden

GERMANY

Tel.: +49-2103-77-800

Fax: +49-2103-77-577

All external materials (i.e. fillers, tapes, sealing compounds, cleaners) must be checked for compatibility with the coating system before use.

Please observe the relevant Technical Data Sheets or seek advice from the Sikkens sales representative or contact the technical centre.

Foam formation during application can be reduced by using defoamer WV 890.

For information concerning the dosage, please see the relevant Technical Data Sheet.

**Coating recommendation** All waterborne and solventborne paint systems can be used on the well dried impregnation. If a separate rot impregnation system is not required, a separate impregnation is not necessary.

We do not recommend using the product in whitish, translucent colour systems such as "opal white" because it could cause yellow discolouration.

**System structure: Dimensional stable wooden constructions**

Impregnation	Impregnation for the wood resistance class 3-5. Do not use more than one BPD-product in ONE system. Cetol WV 885 BPD+
Primer	Rubbol WP 194 Cetol WP 566
Mid coat	Rubbol WM 270 Cetol WM 675 Cetol WM 665 Cetol WM 610
Top coat	Rubbol WF 387 Rubbol WF 382 Rubbol WF 380 Rubbol WF 378 Cetol WF 980 Cetol WF 965 Cetol WF 960 Cetol WF 957 Cetol WF 952 Cetol WF 945

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.