



dipping



application by brush



sanding by hand (dry)



for windows



for doors



stir before use



water thinnable



store and transport in a frost-free area



store in a cool place



cleaning of equipment with water



sikkens
WOOD COATINGS

Cetol WP 575

Product description Waterborne, colourless sanding base coat for constructions made of pine and leaf wood, exterior and interior.

- stabilizing
- quick drying
- easy to apply
- good sanding properties

Colour Colorless

Binder type Acrylic Copolymer

Packaging 5 L

Processing Dipping, brushing

Consumption 40 - 50 ml/m², depending of applied wet film thickness per coat.
(exact values must be established via sample)

Thinning The product is a concentrate and needs to be thinned with water prior to use. The mixing ratio 1:3 (25% base coat: 75% water)

Application temperature 15 - 25 °C for substrate, air and material at approx. 60 % R.H.

Drying times Drying at 23 °C / 50 % R.H.

Dust dry: after approx. 30 minutes

Sandable: after approx. 4 hours

Recoatable: after approx. 4 - 6 hours waterborne

The drying process of the coating depends on the applied wet film thickness and can extend when using timber with a high extract contents or drying in damp/cold conditions. During the drying process one should ensure for adequate temperature and ventilation.

If the drying conditions are not upheld, damages within the coating cannot be warranted.

Cleaning of equipment Clean directly after use with water, if needed with washing up liquid or with ST 830.

Storage The minimum storage stability of sealed containers is 2 years.

Storage temperature: +5 - +30 °C.

After ending of the storage time the product still can be usable, but some attributes may vary from new product.

Therefore such over-stored product has to be applied with special attention.

Opened cans must be sealed correctly! Store in a cool but frost-protected area.

Disposal Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 12.

Hazard identification In accordance with EC guide lines - Material safety data sheet, point 15.

Warning Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

General instructions The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %.

According to the guidelines for window coating systems, published by the Federal German Committee for Paint and Material Value Protection (Instruction Leaflet No. 18), of VOB, Part C, DIN 18363, and the recommendations of the German Institute for Window Technology e.V. in Rosenheim, all wooden constructions in buildings must be coated on all sides with at least one primer and one intermediate coat (minimum dry film thickness 30 µm) before they are incorporated in buildings. The choice and use of the coating system, especially the colour shade, should also be taken into account. Darker shades can increase the surface temperature (up to 80 C).

For use in a technical industrial companies and exclusively released for Sikkens systems recommendations.

VOC guideline EU limit value for this product (Kat. A/e): 150 g/l (2007)/130 g/l (2010). This product contains max. 120 g/l VOC.

Relevant information The here mentioned coating system is only an example, other systems are possible.

All external materials (i.e. fillers, tapes, sealing compounds, cleaners) must be checked for compatibility with the coating system before use.

Please observe the relevant Technical Data Sheets or seek advice from the Sikkens sales representative or contact the technical centre.

Coating recommendation The sanding base coat serves to optically improve the following coating quality aspects. All painting system, opaque and translucent as well as solventborne systems, can be applied on the well dried sanding base coat.

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.

| | | | |
|------------------------------------|---|--------------------------|----------------|
| Akzo Nobel Industrial Coatings Ltd | Unit 4a, Mercer Way, Shadsworth Bus Pk | Blackburn, Lancs, BB12QZ | UNITED KINGDOM |
| Akzo Nobel Industrial Coatings Ltd | Unit 4a, Mercer Way, Shadsworth Bus Pk | Blackburn, Lancs, BB12QZ | Rep of IRELAND |
| Akzo Nobel Wood Coatings GmbH | Düsseldorfer Straße 96-100 | D-40721 Hilden | GERMANY |

Tel. +44 1254 687950

Fax. +44 1254 687960

Tel. +35 (0) 21 4220222

Fax. +35 (0) 21 4220205

Tel.: +49-2103-77-800

Fax: +49-2103-77-577