



stir before use



store and transport
in a frost free area



store in a cool place



cleaning of
equipment with
water



WV 891

Product description Defoamer to decrease foam building during dipping and flow coating application.
Especially suitable for Cetol WM 675.

Colour milky white

Packaging 5 L

Processing For a better distribution of the defoamer, it is recommended to pre-mix the defoamer in water in a ratio of 1:5 and stir thoroughly

Consumption additive amount: 0,1-0,5%

Cleaning of equipment Clean directly after use with water, if needed with washing up liquid or with ST 830.

Storage The minimum storage stability of sealed containers is 2 years.

Storage temperature: +5 - +30 °C.

After ending of the storage time the product still can be usable, but some attributes may vary from new product.

Therefore such over-stored product has to be applied with special attention.

Opened cans must be sealed correctly! Store in a cool but frost-protected area.

Disposal Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 12.

Hazard identification In accordance with EC guide lines - Material safety data sheet, point 15.

Warning Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

VOC guideline Out of scope.

General instructions For use in technical industrial companies and intended only for recommended Sikkens systems.

Relevant information The defoamer may separate into two phases - that is why the canister must be shaken well before use.

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.