



dipping



application by brush



for windows



for doors



limited dimension
stable wooden
constructions



non dimension
stable wooden
constructions



stir before use



store and transport
in a frost-free area



store in a cool place



Adjust viscosity with
ST 825



cleaning of
equipment with ST
825



sikkens
WOOD COATINGS

Rubbol SP 110

Product description Solventborne, white base coat for constructions made of pine and leaf wood, exterior and interior.

- stabilizing
- wood moisture regulating
- good edge covering
- high filling properties

Colour White

Binder type Alkyd resin

Pigments Titanium dioxide

Packaging 20 L

Processing Dipping, brushing

Consumption 50 - 160 ml/m², depending on application method, type and absorption properties of wood (exact values must be established through a sample)

Thinning Adjust with ST 825* to approx. 15 seconds in a DIN 4 mm cup at 20 C material temperature.

Application temperature +5 - 30 °C for substrate, air and material at approx. 60 % R.H.

Drying times The drying process of the coating depends on the applied wet film thickness and can extend when using timber with a high extract contents or drying in damp/cold conditions. During the drying process one should ensure for adequate temperature and ventilation.

If the drying conditions are not upheld, damages within the coating cannot be warranted.

Drying at 23 °C / 50 % R.H.

Dust dry: after approx. 2 hours

Sandable: after approx. 18 hours

Recoatibility of dipp primers: after approx. 24 hours, brush application earliest after 3 days

Cleaning of equipment With the thinner ST 825 or Turpentine.

Storage A dipping tank containing material must be covered correctly and stirred or circulated regularly.

The minimum storage stability of sealed containers is 2 years.

Storage temperature: +5 - +30 °C.

After ending of the storage time the product still can be usable, but some attributes may vary from new product.

Therefore such over-stored product has to be applied with special attention.

Opened cans must be sealed correctly! Store in a cool but frost-protected area.

Disposal Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 11.

Hazard identification In accordance with EC guide lines - Material safety data sheet, point 15.

Warning The substance is not to be employed near water courses. They are only to be used according to the instructions and in the permitted areas. Misuse can lead to health and environmental damages.

Not for use for timber, which has direct contact with food or food preparation.

Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

This product can, if distributed finely, due to the type of binder have the risk of self combustion. Dry spray dust and thin dust deposits are flammable and therefore immediately to remove. When cleaning, it is important to collect deposits and cleaning materials and place them in lockable, non-flammable containers. After cleaning the waste dustbins should be closed air tight.

General instructions The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %.

According to the guidelines for window coating systems, published by the Federal German Committee for Paint and Material Value Protection (Instruction Leaflet No. 18), of VOB, Part C, DIN 18363, and the recommendations of the German Institute for Window Technology e.V. in Rosenheim, all wooden constructions in buildings must be coated on all sides with at least one primer and one intermediate coat (minimum dry film thickness 30 µm) before they are incorporated in buildings. The choice and use of the coating system, especially the colour shade, should also be taken into account. Darker shades can increase the surface temperature (up to 80 C).

For use in a technical industrial companies and exclusively released for Sikkens systems recommendations.

To ensure a correct adhesion of the following coating system, the paint system should not be sanded down to the substrate.

With some wood species, especially hardwoods, discolouration can appear due to natural wood extractives.

VOC guideline EU limit value for this product (Kat. A(h)): 750 g/l (2007)/750 g/l (2010). This product contains max. 675 g/l VOC.

Relevant information The here mentioned coating system is only an example, other systems are possible.

All external materials (i.e. fillers, tapes, sealing compounds, cleaners) must be checked for compatibility with the coating system before use.

Please observe the relevant Technical Data Sheets or seek advice from the Sikkens sales representative or contact the technical centre.

Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ
 Bus Pk
 Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ
 Bus Pk
 Akzo Nobel Wood Coatings GmbH Düsseldorf StraÙe 96-100 D-40721 Hilden

UNITED KINGDOM

Tel. +44 1254 687950

Fax. +44 1254 687960

Rep of IRELAND

Tel. +35 (0) 21 4220222

Fax. +35 (0) 21 4220205

GERMANY

Tel.: +49-2103-77-800

Fax: +49-2103-77-577

System structure: Dimensional stable wooden constructions

Impregnation	Impregnation for the wood resistance class 3-5. Do not use more than one BPD-product in ONE system. Cetol WV 880 BPD Cetol WV 885 BPD+
Primer	Rubbol SP 110
Mid coat	Rubbol WM 270 Cetol WM 665
Top coat	Rubbol WF 387 Rubbol WF 382 Rubbol WF 380 Rubbol WF 378

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.