



spraying



for doors



Mixing ratio



stir before use



water thinnable

store and transport
in a frost free area

store in a cool place

sikkens

WOOD COATINGS

cleaning of
equipment with
watershake well before
usewear protective
glovesWear protective
mask

NEU!

Cetol WF 990

Product description Waterborne two-component, lightfast clear PUR lacquer as finishing coat for doors, window-sills and metallic with high demands on mechanical and chemical resistance. To use with hardener WV 860.

- high transparency
- good leveling
- good mechanical resistance
- Safety of Toys (according to EN 71, part 3)

Colour Colorless

Gloss level Satin-matt

Binder type Polyurethane

Packaging 5 L

Attention: can has to shaken well before use!

Processing Mixing ratio 5:1 (5 parts of lacquer: 1 part of hardener)

Spraying

Wet film thickness: 1 x 100 up to 120 µm max.

Pot life: approx. 4 h after the components have been mixed

Consumption 100 - 150 ml/m² depending on applied wet film thickness per coat without losses.

Thinning Do not thin down

Application temperature 15 - 25 °C for substrate, air and material at approx. 60 % R.H.

Drying times The drying process of the coating depends on the applied wet film thickness and can extend when using timber with a high extract contents or drying in damp/cold conditions. During the drying process one should ensure for adequate temperature and ventilation.

If the drying conditions are not upheld, damages within the coating cannot be warranted.

Drying at 23 °C / 50 % R.H.

Dust dry: after approx. 30 minutes

Touch-dry: after approx. 1 hour

Sandable: after approx. 4 hours

Transportable: after approx. 12 hours

After a minimum drying time of 4 hours up to a maximum of 24 hours, the next coat of Cetol WF 990 can be applied without intermediate sanding. If the next coat should be applied later, e.g., after drying overnight, intermediate sanding must be carried out to ensure proper adhesion. Therefore we recommend using a sanding paper with fine grain.

Cleaning of equipment Clean directly after use with water, if needed with washing up liquid or with ST 830.

Storage The minimum storage stability of sealed containers is 1 year.

Storage temperature: +5 - +30 °C.

After ending of the storage time the product still can be usable, but some attributes may vary from new product.

Therefore such over-stored product has to be applied with special attention.

Opened cans must be sealed correctly! Store in a cool but frost-protected area.

PUR hardeners are sensitive to moisture. Please, store the hardener always in tightly closed containers.

Disposal Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 12.

Hazard identification In accordance with EC guide lines - Material safety data sheet, point 15.

Warning Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

General instructions For use in technical industrial companies and intended only for recommended Sikkens systems.

The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %.

VOC guideline EU limit value for this product (cat. A/e): 130 g/l (2010)

This product contains max. 74 g/l VOC.

Relevant information Whenever polyurethane (PUR) material is to be over coated, the surface has to be sanded and sanding dust removed thoroughly just before commencing with further treatment to guarantee perfect bonding.

Cetol WF 990 may only be applied on the top coats mentioned in the following. The finish coats will not be sanded before overcoating with Cetol WF 990 !

All external materials (e.g., fillers, adhesive tapes, sealing compounds, cleaners, etc.) must generally be checked for compatibility.

Please refer to the corresponding Technical Data Sheets and ask your Sikkens field representative or the factory for advice with regard to the coating system.

Coating recommendation When coating hardwood, we recommend using Rubbol WM 270 or Cetol WM 610 as pore-filling midcoat. For best surface appearance, pores must be closed.

Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ

Bus Pk

Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ

Bus Pk

Akzo Nobel Wood Coatings GmbH Düsseldorf StraÙe 96-100

D-40721 Hilden

UNITED KINGDOM

Tel. +44 1254 687950

Fax. +44 1254 687960

Rep of IRELAND

Tel. +35 (0) 21 4220222

Fax. +35 (0) 21 4220205

GERMANY

Tel.: +49-2103-77-800

Fax: +49-2103-77-577

System structure: Dimensional stable wooden constructions

Impregnation	Impregnation for the wood resistance class 3-5. Do not use more than one BPD-product in ONE system. Cetol WV 885 BPD+ Cetol WV 880 BPD
Primer	Rubbol WP 193 Rubbol WP 151 Cetol WP 566
Mid coat	Rubbol WF 382 Rubbol WF 380 Rubbol WF 378 Cetol WF 965 Cetol WF 960 Cetol WF 957 Cetol WF 952 Rubbol WF 387 Rubbol WF 390 metallic
Top coat	Cetol WF 990

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.