



application by brush



limited dimension  
stable wooden  
constructions



non dimension  
stable wooden  
constructions



stir before use



store in a cool place



cleaning of  
equipment with ST  
825

## Cetol SF 711

**Product description** Solventborne, satin gloss thinn build varnish as a base - mid and finish coat for wooden constructions ( profile boards, fascia, gable, rafters, etc.) use as a one pot system also for renovating coats and repairs of old intact paint systems.

- moisture permeability
- easy to apply
- good weather resistance

**Colour** With the choice of the different translucent colours, one should observe the Rosenheimer paint classification table. All translucent colours can be mixed with each other. The optical appearance of different systems can differ depending on substrate and wet film thicknesses, for this reason one should make trials before application.

Dark translucent colours give better weather durability than light colours. Colourless systems are not suitable for exterior. Timbers which contain extractives i.e. Oak, Larch or tropical woods can cause discolouring - these can appear after weathering. K006 light Oak, K010 Walnut, K077 Deal, K085 Teak, other colours on request.

**Gloss level** Satin-gloss

**Binder type** Alkyd resin

**Pigments** Light genuine, weather resistant translucent pigments

**Packaging** 2,5 L, 10 L

**Processing** Brushing

Only use in thinn coats

**Consumption** 50 - 60 ml/m<sup>2</sup>, depending of applied wet film thickness per coat.  
(exact values must be established via sample)

**Thinning** Do not thin down

**Application temperature** +5 - 30 °C for substrate, air and material at approx. 60 % R.H.

**Drying times** The drying process of the coating depends on the applied wet film thickness and can extend when using timber with a high extract contents or drying in damp/cold conditions. During the drying process one should ensure for adequate temperature and ventilation.

If the drying conditions are not upheld, damages within the coating cannot be warranted.

Drying at 23 °C / 50 % R.H.

Dust dry: after approx. 6 - 8 hours

Sandable: after approx. 24 hours

Recoatable: after approx. 24 hours

**Cleaning of equipment** With the thinner ST 825 or Turpentine.

**Storage** The minimum storage stability of sealed containers is 2 years.

Storage temperature: +5 - +30 °C.

After ending of the storage time the product still can be usable, but some attributes may vary from new product.

Therefore such over-stored product has to be applied with special attention.

Opened cans must be sealed correctly! Store in a cool but frost-protected area.

**Disposal** Only residue emptied cans can be disposed via recycling. Liquid wastes must be disposed of according to national regulations or according to EU-disposal key 08 01 11.

**Hazard identification** In accordance with EC guide lines - Material safety data sheet, point 15.

**Warning** Before use, read the identification and product information. Even when working with low emission products one should take care of the customary protection measures.

This product can, if distributed finely, due to the type of binder have the risk of self combustion. Dry spray dust and thin dust deposits are flammable and therefore immediately to remove. When cleaning, it is important to collect deposits and cleaning materials and place them in lockable, non-flammable containers. After cleaning the waste dustbins should be closed air tight.

**General instructions** The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %.

According to the guidelines for window coating systems, published by the Federal German Committee for Paint and Material Value Protection (Instruction Leaflet No. 18), of VOB, Part C, DIN 18363, and the recommendations of the German Institute for Window Technology e.V. in Rosenheim, all wooden constructions in buildings must be coated on all sides with at least one primer and one intermediate coat (minimum dry film thickness 30 µm) before they are incorporated in buildings. The choice and use of the coating system, especially the colour shade, should also be taken into account. Darker shades can increase the surface temperature (up to 80 °C).

For use in a technical industrial companies and exclusively released for Sikkens systems recommendations.

To ensure a correct adhesion of the following coating system, the paint system should not be sanded down to the substrate.

**VOC guideline** EU limit value for this product. (kat.A/e):500g/L (2007)/ 400g/L (2010). This product contains max. 400 g/l VOC.

**Relevant information** The here mentioned coating system is only an example, other systems are possible.

All external materials (i.e. fillers, tapes, sealing compounds, cleaners) must be checked for compatibility with the coating system before use.

Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ

Bus Pk

UNITED KINGDOM

Tel. +44 1254 687950

Fax. +44 1254 687960

Akzo Nobel Industrial Coatings Ltd Unit 4a, Mercer Way, Shadsworth Blackburn, Lancs, BB12QZ

Bus Pk

Rep of IRELAND

Tel. +35 (0) 21 4220222

Fax. +35 (0) 21 4220205

Akzo Nobel Wood Coatings GmbH Düsseldorf StraÙe 96-100

D-40721 Hilden

GERMANY

Tel.: +49-2103-77-800

Fax: +49-2103-77-577

Please observe the relevant Technical Data Sheets or seek advice from the Sikkens sales representative or contact the technical centre.

**Coating recommendation** Renovation systems:  
 Open joints and small cracks can be closed with Kodrin WV Spachtel. Substrate preparation: non intact, old and loose coatings must be completely removed. Intact coating should be completely sanded. Raw wood must be impregnated where necessary.

**System structure: Dimensional semi stable wooden constructions and not stable constructions.**

Impregnation	Impregnation for the wood resistance class 3-5. Do not use more than one BPD-product in ONE system. Cetol WV 885 BPD+
Primer	Cetol SF 711
Mid coat	Cetol SF 711
Top coat	Cetol SF 711

All details on our products contained in this publication do not represent details of the quality of the goods. The quality, suitability, qualification and function intended use of our goods shall be determined exclusively in accordance with the product descriptions based on the respective sales agreements. In each case, deviations typical of the sector shall be admissible, unless agreed in writing otherwise. All details correspond to today's state of technology. We make no claim as to the completeness of the stated coating installations; they are stated merely as possible examples. Due to the large number of substrates and object conditions, the buyer/user shall not be released from his/her obligation to check our raw materials in a workmanlike manner for their suitability for the intended purpose on his/her own responsibility subject to the respective property conditions and process these in accordance with the respective state of technology. In other respects, our standard terms and conditions of sale apply. Upon the appearance of a new edition, this publication shall lose its validity.

Akzo Nobel Industrial Coatings Ltd	Unit 4a, Mercer Way, Shadsworth Bus Pk	Blackburn, Lancs, BB12QZ	UNITED KINGDOM	Tel. +44 1254 687950	Fax. +44 1254 687960
Akzo Nobel Industrial Coatings Ltd	Unit 4a, Mercer Way, Shadsworth Bus Pk	Blackburn, Lancs, BB12QZ	Rep of IRELAND	Tel. +35 (0) 21 4220222	Fax. +35 (0) 21 4220205
Akzo Nobel Wood Coatings GmbH	Düsseldorfer Straße 96-100	D-40721 Hilden	GERMANY	Tel.: +49-2103-77-800	Fax: +49-2103-77-577